



GAMMA RAY INDUCED THERMOLUMINESCENCE

PROPERTIES OF $\text{ZrO}_2\text{:Eu}^{3+}$, Dy^{3+} PHOSPHOR

Raunak Kumar Tamrakar¹, Kanchan Upadhyay²

¹Department of Applied Physics, Bhilai Institute of Technology (Seth Balkrishan Memorial),

Near Bhilai House, Durg, C.G. (India)

²Department of Chemistry, Shri Shanakaracharya Vidhyalay, Aamdi nagar, Hudco, Bhilai (India)

ABSTRACT

The present paper reports the synthesis, characterization and Gamma dose induced thermoluminescence properties of $\text{ZrO}_2\text{:Eu}^{3+}$, Dy^{3+} phosphor. The sample was prepared by solid state reaction method. The particle size of prepared phosphor was calculated by XRD technique and Confirmed by Scanning electron microscope. The luminescence property of prepared phosphor examined by thermoluminescence technique and Computerized Deconvolution method was applied to obtain the deconvoluted curve. For recording TL glow curve 0.5mg phosphor was irradiated by 0.5 kGy gamma radiations at 3°Cs^{-1} heating rate. Trapping parameters were calculated for deconvoluted TL glow curve.

Keywords: $\text{ZrO}_2\text{:Eu}^{3+}$, Dy^{3+} Phosphor, XRD, SEM, Gamma radiation, Thermoluminescence, Deconvolution.

I. INTRODUCTION

Semiconductors and insulator materials like Zirconium, are remarkable materials due to their excellent mechanical, electrical, thermal and optical properties. Recently, nanoparticles have been recognized to take potential in the area of photonic applications [1-11]. Some researches have done on thermoluminescent properties of zirconium oxide based phosphors. Zirconia can adopt three different crystalline structures: cubic, tetragonal, and monoclinic, depend on the synthesis temperature [4,6]. Only few research works has been done on the thermoluminescence properties of this material. In the present work, face centered crystalline phase of ZrO_2 was successfully synthesized by simple solid state reaction method [5,8] and its thermoluminescence property was investigated. The synthesized phosphor's structural characterizations were done by using powder X-ray diffraction (PXRD) and scanning electron microscopy (SEM). To the best of our knowledge, no thermoluminescence (TL) studies on $\text{ZrO}_2\text{:Eu}^{3+}$, Dy^{3+} phosphor have been reported for gamma dose. Europium and dysprosium are good dopants for optical properties [12] The thermoluminescence studies were carried out using TLD reader I1009 supplied by Nucleonix Sys. Pvt. Ltd. Hyderabad [13]. The heating rate used for TL measurement is 3°C/s . Computerized glow curve deconvolution was applied on the TL glow curve and kinetic parameters were calculated by using Chen's peak shape method [14].

II. SYNTHESIS OF $\text{ZrO}_2\text{:Eu}^{3+}, \text{Dy}^{3+}$

The conventional solid state reaction process is used to prepare the $\text{ZrO}_2\text{:Eu}^{3+}, \text{Dy}^{3+}$ phosphor. Oxide of zirconium, europium and dysprosium with high purity (sigma Aldrich 99.99%) were mixed in stoichiometric ratio by dry grinding in mortar & pestle for nearly 60 minutes. The mixture is taken in quartz boat and is fired in air at 1200°C for 2 hours in presence of boric acid as a flux. We prepared the phosphor with fix concentration of Eu^{3+} and Dy^{3+} at 1mol%. Finally $\text{ZrO}_2\text{:Eu}^{3+}, \text{Dy}^{3+}$ phosphor were obtained by solid state reaction method [11, 15-19].

III. RESULT AND DISCUSSION

3.1 Structural Characterization

Fig.1 shows the XRD patterns of the $\text{ZrO}_2\text{:Eu}^{3+}, \text{Dy}^{3+}$. Diffraction peaks are well matched with ICDD card no. 89- 9069 showing a face centred cubic structure [11]. The size of the crystal has been computed from the full width half maximum (FWHM) of the all peaks using the Scherer's formula $d=k\lambda/\beta\cos\theta$ [20]. Where, D is the average crystal size perpendicular to the reflecting planes, k is the constant the value of K is .89, λ is the X-ray wavelength, β is the FWHM, and θ is the diffraction angle. The particle size of the sample is found around 77nm.




Fig 1 X-ray diffraction pattern of $\text{ZrO}_2\text{:Eu}^{3+}(1\%), \text{Dy}^{3+}(1\%)$

3.2 Scanning Electron Microscope (Sem)

Figure 2 shows SEM images of prepared phosphors. As this figures shows, the grain size of $\text{ZrO}_2\text{:Eu}^{3+}, \text{Dy}^{3+}$ near to the XRD results.




Figure 2. SEM image of $\text{ZrO}_2:\text{Eu}^{3+}(1\%), \text{Dy}^{3+}(1\%)$

3.3 Thermo Luminescence Studies

Thermoluminescence glow peak of $\text{ZrO}_2:\text{Eu}^{3+}; \text{Dy}^{3+}$ has been recorded under 0.5kGy gamma dose. The glow peak was recorded for 3°C s^{-1} heating rate. The deconvoluted glow peak was found at 129°C 186 °C and 236 °C (Fig 3).




Figure 4. Deconvoluted TL glow curve of $\text{ZrO}_2:\text{Eu}^{3+}(1\%) \text{Dy}^{3+}(1\%)$ for .5kGy gamma ray

Table 1 shows the evaluated kinetic parameters of prepared phosphor. Kinetic parameters determination has always been an active area of research for better understanding of the TL mechanism [21-29]. The trap depth and the frequency factor of isolated peaks were evaluated using the Chen's peak shape method and others [14, 22, 30-32].


Table :- 1 Kinetic parameters for $\text{ZrO}_2\text{:Eu}^{3+}$ (1%), Dy^{3+} (1%)

Peak	T_1	T_m	T_2	τ	δ	ω	$\mu = \delta / \omega$	Activation Energy (E)	Frequency Factor (s^{-1})
Peak 1	104	129	159	25	30	55	0.545	0.848	7.2×10^{11}
Peak 2	157	186	215	29	29	58	0.5	0.942	3.16×10^{11}
Peak 3	218	236	255	18	19	37	0.514	1.874	8.45×10^{19}

IV. CONCLUSIONS

The $\text{ZrO}_2\text{:Eu}^{3+}$ (1%), Dy^{3+} (1%) phosphor was synthesized by simple solid state reaction method. The characterization by XRD shows the sample was cubic in structure with 77 nm crystal size. The particle size was confirmed by SEM images. Sample shows good TL response and the kinetic parameters are also evaluated shows the second order of kinetics for deconvoluted three peaks. The activation energy is found in the range of 0.848 to 1.874 and frequency factor (s) in the range of 3.16×10^{11} to $8.45 \times 10^{19} \text{ s}^{-1}$.

REFERENCES

- [1]. R. N. Bhargava, D. Gallagher, X. Hong, A. Nurmikko, Phys. Rev. Lett. 72 (1994) 416.
- [2]. R. K. Tamrakar, Studies on Absorption Spectra of Mn Doped CdS Nanoparticles, (LAP Lambert Academic Publishing, Verlag, 2012). ISBN 978-3-659-26222-7.
- [3]. D. P. Bisen, R. Sharmab, N. Brahme, R. K. Tamrakar. Effect of Temperature on the synthesis Of Cds:Mn doped nanoparticles, Chalcogenide Letters Vol. 6, No. 9, September 2009, p. 427 – 431.
- [4]. Chen Limiao, Liu Younian, Li Yadong , Preparation and characterization of $\text{ZrO}_2\text{:Eu}^{3+}$ phosphors, Journal of Alloys and Compounds 381 (2004) 266-271.
- [5]. R. K. Tamrakar D P Bisen, K Upadhyay, S. Tiwari, Synthesis and thermoluminescence behavior of $\text{ZrO}_2\text{:Eu}^{3+}$ with variable concentration of Eu^{3+} doped phosphor, Journal of Radiation Research and Applied Sciences (2014), 7 (2014) 486-490.
- [6]. N. Tiwari, R.K. Kuraria, R. K. Tamrakar, Thermoluminescence glow curve for UV induced $\text{ZrO}_2\text{:Ti}$ phosphor with variable concentration of dopant and various heating rate, Journal of Radiation Research and Applied Sciences (2014), 7 (2014) 542-549 DOI: 10.1016/j.jrras.2014.09.006
- [7]. R. K. Tamrakar, N. Tiwari, R. K. Kuraria, D. P Bisen, V. Dubey, K. Upadhyay, Effect of annealing temperature on thermoluminescence glow curve for UV and gamma ray induced $\text{ZrO}_2\text{:Ti}$ phosphor, Journal of Radiation Research and Applied Sciences (2014) 8(1), 1-10, <http://dx.doi.org/10.1016/j.jrras.2014.10.005>
- [8]. R. K. Tamrkar, D. P. Bisen, K. Upahdyay, Photoluminescence behavior of $\text{ZrO}_2\text{:Eu}^{3+}$ with variable concentration of Eu^{3+} doped phosphor, Journal of Radiation Research and Applied Sciences , 8 (2015) 11-16.



- [9]. R. K. Tamrakar, N. Tiwari, V. Dubey, K. Upadhyay, Infrared spectroscopy and luminescence spectra of Yb^{3+} doped ZrO_2 nanophosphor, Journal of Radiation Research and Applied Sciences, 8 (2015) 399-403.
- [10]. C. S. Robinson, R. K. Tamrakar, D. P. Bisen, & N. Brahme, Thermoluminescence Study of $\text{ZrO}_2: \text{Er}^{3+}$, Yb^{3+} , J. Pure Appl. & Ind. Phys, 2 (3A), 310-314, ISSN : 2229-7596
- [11]. J. Kaur, Y. Parganiha, V. Dubey, D. Singh, D. Chandrakar, Synthesis, characterization and luminescence behavior of $\text{ZrO}_2: \text{Eu}^{3+}$, Dy^{3+} with variable concentration of Eu and Dy doped Phosphor Superlattices and Microstructures 73, 38-53
- [12]. I. P. Sahu, D. P. Bisen, N. Brahme, L. Wanjari, R. K. Tamrakar, Structural Characterization and Luminescence Properties of Bluish-Green Emitting $\text{SrCaMgSi}_2\text{O}_7: \text{Eu}^{2+}$, Dy^{3+} Phosphor by Solid State Reaction Method, Research on Chemical Intermediate, DOI:10.1007/s11164-015-1929-1, Springer Publication,
- [13]. R. K. Tamrakar, UV-irradiated thermoluminescence studies of bulk CdS with trap parameter Res Chem Intermed (2015) 41:43–48
- [14]. R. Chen, Y. Krish, Analysis of Thermally Stimulated Process, Pergamon Press, Oxford, 1981, 159–161
- [15]. R. K. Tamrakar, K. Upadhyay, & D. P. Bisen, Gamma ray induced thermoluminescence studies of yttrium (III) oxide nanopowders doped with gadolinium, Journal of Radiation Research and Applied Sciences (2014), 7 (2014) 526-531, DOI: 10.1016/j.jrras.2014.08.012.
- [16]. I. P. Sahu, D. P. Bisen, N. Brahme and R. K. Tamrakar Luminescence enhancement of bluish-green $\text{Sr}_2\text{Al}_2\text{SiO}_7: \text{Eu}^{2+}$ phosphor by dysprosium co-doping, Journal of Luminescence 167(2015) 278-288.
- [17]. R. K. Tamrakar, D. P. Bisen, Thermoluminescence studies of ultraviolet and gamma irradiated erbium (III)- and ytterbium (III)- doped gadolinium oxide phosphors, Materials Science in Semiconductor Processing 33 (2015) 169-188
- [18]. R. K. Tamrakar, D. P. Bisen, I. P. Sahu, & N. Brahme, UV and gamma ray induced thermoluminescence properties of cubic $\text{Gd}_2\text{O}_3: \text{Er}^{3+}$ phosphor, 30 July (2014). Journal of Radiation Research and Applied Sciences, 7(4), 417e429. <http://dx.doi.org/10.1016/j.jrras.2014.07.003>
- [19]. R. K. Tamrakar, D. P. Bisen, C. S. Robinson, I. P. Sahu, and N. Brahme, Ytterbium Doped Gadolinium Oxide ($\text{Gd}_2\text{O}_3: \text{Yb}^{3+}$) Phosphor: Topology, Morphology, and Luminescence Behaviour in Hindawi Publishing Corporation Indian Journal of Materials Science Volume 2014, Article ID 396147, 7 pages, Accepted 4 February 2014.
- [20]. A. Guinier, X-ray diffraction, Freeman, San Francisco, 1963.
- [21]. R. K. Tamrakar, D. P. Bisen, Optical and kinetic studies of CdS: Cu nanoparticles, Res. Chem. Intermed. 39 (2013) 3043–3048.
- [22]. K. S. V. Nambi Thermoluminescence its understanding and applications, Health Physics Division, Bhabha Atomic Research Centre, Brazil, 1977.
- [23]. R. K. Tamrakar, D. P. Bisen and Nameeta Brahme, Characterization and luminescence properties of Gd_2O_3 Phosphor, Res Chem Intermed (2014) 40:1771–1779.
- [24]. Numan Sala, Sami S Habib, Zishan H. Khan, Fathi Djouider, Thermoluminescence and photoluminescence of ZrO_2 nanoparticles, Radiation Physics and Chemistry 80 (2011) 923–929



- [25]. R. K. Tamrakar, and D. P. Bisen Combustion synthesis and optical properties of ceria doped gadolinium oxide nano powder AIP Conf. Proc. 1536, 273 (2013); doi: 10.1063/1.4810206.
- [26]. R. K. Tamkrakar, V. Dubey, Swamy N. Kumar, N. Tiwari, S. V. N. Pammi ,P. V. Ramakrishna, Thermoluminescence studies of UV-irradiated $Y_2O_3: Eu^{3+}$ doped phosphor, Research on Chemical Intermediates 39(8) (2013)3919-3923.
- [27]. R. K. Tamrakar , D. P. Bisen, I. P. Sahu, N. Brahme, UV and gamma ray induced thermoluminescence properties of cubic $Gd_2O_3:Er^{3+}$ phosphor, Journal of Radiation Research and Applied Sciences (2014), 7(4), 417-429
- [28]. R. K.Tamrakar, D. P. Bisen, Thermoluminescence studies of ultraviolet and gamma irradiated erbium (III)-and ytterbium (III)-doped gadolinium oxide phosphors, Materials Science in Semiconductor Processing, 33, 169-188(2015).
- [29]. R. K. Tamrakar, Thermoluminescence studies of copper-doped cadmium sulphide nanoparticles with trap depth parameters, Research on Chemical Intermediates, 39(9) 4239-4245.
- [30]. R. Chen and S.W.S. McKeever, Theory of Thermoluminescence and Related Phenomena. World Scientific Publications, London, NJ, Singapore, 576pp, Oct. 1997
- [31]. R. Chen and V. Pagonis, Thermally and Optically Stimulated Luminescence: A Simulation Approach, Wiley, Chichester, 434pp, 2011.
- [32]. R. Chen and G.A. Haber, Calculation of Glow Curves Activation Energies by Numerical Initial Rise Method, Chem. Phys. Lett. 2, 483-485 (1968).